



## TECHNICAL INFORMATION Durocoat W 1000

---

# SEALER – W 1000

---

Single Component Water Based Sealer.

### PRINCIPAL USE

As a transparent undercoat for wooden surfaces intended for interior use such as furniture, doors, etc.

Viscosity (DIN 6) : 80 ± 10 KU

VOC Values (g/Lt): 70

### SPECIAL FEATURES

As a fast drying, easily sanded sealer that provides a durable surface for the finishing varnish. It is highly transparent, non-yellowing, odourless product friendly for the user and the environment.

### INFORMATION

High levels of relative humidity will increase the drying time. Avoid application of this product when the relative humidity exceeds 70%. The ambient temperature should not be less than 10°C during the application of the product.

### CHEMICAL & PHYSICAL CHARACTERISTICS

Solid Content :	35 ± 1 %
Drying time at 20°C	
Dust free	20-30 min.
Touch dry	40-50 min
Through dry	2-3 hours
Coverage :	8 - 10 m <sup>2</sup> /Lt
Specific Weight :	1.035+0,005 Kg/L

### APPLICATION INSTRUCTIONS

This product can be applied by an airless gun or conventional gun. If applied by airless gun, it must be diluted 5-10% with water. If applied by a conventional gun, a nozzle of 1,8-2,0 should be used, the air pressure should be regulated to 3-4bar and the product must be diluted 10-20% with water. The surface should be sanded with NO. 240-320 type of abrasive prior to the application of the finishing coat.