

**TECHNICAL DATA SHEET****PRODUCT**            **EP200 2 - PACK CLEAR EPOXY PRIMER - SEALER.****DESCRIPTION**

EP200 Two-pack epoxy clear primer sealer is recommended for use as a tie coat to maximise the adhesion and water impermeability of Urethane topcoats with difficult substrates such as concrete and masonry surfaces.

It is especially suitable in applications requiring a high degree of solvent and chemical resistance for industrial applications or as a base component in decorative / protective polyurethane finishes for the transport sector.

**PROPERTIES****COLOUR**

Clear

**GLOSS LEVEL**

Gloss

**WEATHERING**

Not Applicable (usually top coated)

**CHEMICAL  
RESISTANCE**

Excellent (weak organic acids and common alkalis)

**SOLVENT  
RESISTANCE**

Excellent (unaffected by most common organic solvents)

**ABRASION  
RESISTANCE**

Very good - excellent.

**TEMPERATURE  
RANGE**

Up to 110 °C. (dry).

**TECHNICAL DATA  
RECOMMENDED****FILM BUILD**

120 microns (wet)

60 microns (dry) per coat.

**VOLUME SOLIDS**

50%

( on non absorbent substrate)

**THEORETICAL  
COVERAGE**

Typically 9 sq metres per litre at 100 - 120 microns wet. (100% transfer basis).

**COMPONENTS**

Two

**MIXING RATIO**

4A : 1B

**TECHNICAL DATA SHEET**  
**EP200 2-PACK CLEAR EPOXY PRIMER -SEALER**

<b>DRYING AT 25 °C</b>	Touch dry: 2 hrs	Handleable: 16 hrs
	Recoat: 8 - 10 hrs	Full cure: 7 days
<b>POT LIFE AT 25 °C</b>	8 hrs (will reduce as temperature increases)	
<b>APPLICATION METHODS</b>	Brush, roller, air or airless spray.	
<b>FLASHPOINT</b>	27 °C.	
<b>RECOATABILITY</b>	Recoat within 5 days.	
<b>SHELF LIFE</b>	12 months (minimum) in original containers	
<b>PACKAGING</b>	Part A 1 lt. 4 lt. 20 lt.	Part B 1 lt. 5 lt.

**SYSTEM RECOMMENDATIONS**

<b><u>SUBSTRATE</u></b>	<b><u>PREPARATION</u></b>	<b><u>COATING SEQUENCE</u></b>	<b><u>FILM BUILD WET (DRY)</u></b>
<b>CONCRETE</b>	Fresh concrete should be acid washed.	1st coat : EP200 2-pack Epoxy Sealer	80 - 100 (30 - 40) microns
<b>OR MASONRY</b>	Remove loose material and dust.	Finish coat : UT110 Series Acrylic topcoats	125 (50) microns.

**SURFACE PREPARATION**

**CONCRETE / MASONRY**

Acid wash new surfaces using dilute hydrochloric acid.  
 Wash with fresh water and allow to fully dry.  
 Old surfaces must be free of all foreign matter, oil, grease, scale etc., which should be removed using traditional method such as solvent wiping , steam degreasing or water blasting.  
 Any loose or crumbling material will need to be secured.

**TECHNICAL DATA SHEET**  
**EP200 2-PACK CLEAR EPOXY PRIMER -SEALER**

**APPLICATION****MIXING**

Stir each of the components till homogenous.  
Mix all base and hardener components until fully blended.  
Allow induction time of 15 - 20 minutes prior to use.  
For smaller quantities mix 1 parts of base to 1 part hardener by volume.

**THINNING**

Use recommended thinner only, up to a maximum of 10 by volume depending on method of application employed.

**BRUSH  
OR ROLLER**

Use brush for small or difficult areas.  
Short nap roller is recommended with two coats for best result and even finish.  
Wash up with EP100 Epoxy Thinner.

**AIRLESS**

Standard airless equipment using 28:1 pump ratio and fluid tip in range 475 - 525 microns (0.019-.021 inches) and supply air at 520 - 650 kPa (80 - 100p.s.i).  
Thin as necessary with EP100 Epoxy Thinner.

**EQUIPMENT  
CLEANUP**

All equipment should be thoroughly cleaned with EP100 Epoxy Thinner.

**TECHNICAL DATA SHEET**  
**EP200 2-PACK CLEAR EPOXY PRIMER -SEALER**

**PRECAUTIONS****SAFETY**

Provide adequate ventilation during use.  
Airflow should be adequate to ensure a comfortable working atmosphere.  
When spray painting, users should comply with the provisions of the State Spray Painting Regulations.  
Where this is not possible, operators must use an air supplied respirator complying with Australian Standards AS1715 and AS1716.

This product is flammable and all sources of ignition (flame, pilot lights, furnaces, spark producing switches etc.) must be eliminated in, or near, the application area.  
**DO NOT SMOKE.**

This product is polyamide catalysed and the necessary precautions must be observed when handling this material.

Avoid contact with skin and eyes.

Wear protective goggles and gloves when handling the material.

In the case of skin contact, remove contaminated clothing and wash skin thoroughly with clean water.

Seek medical attention if eyes are affected by splashes or fumes.

**GENERAL**

Freshly mixed material must not be added to material which has been in use for some time.

Rate of cure is dependent upon temperature.

Do not apply this product at temperatures below 10 °C or relative humidities > 85%.

Ensure maximum recoat interval is not exceeded otherwise surface must be lightly abraded and then dusted to ensure maximum intercoat adhesion.

Shelf life is normally 12 months but depends on storage conditions.

**DANGEROUS GOODS**

Part A	Class 3.1	UN	1263	PAINT	HFP
Part B	Class 3.2	UN	1866	PAINT	HFP

This data sheet is based on information in BC Coatings possession at date of issue.

BC Coatings supplies its products only on condition that the consumer is satisfied as to the performance of the product in meeting his particular requirements.

061207